

RADIATION ATTENUATING EXAMINATION & SURGICAL GLOVES POWDERFREE

APPLICATION - SPECIFIC FOR PROCEDURES REQUIRING ENHANCED TACTILE SENSITIVITY

- Anatomically correct fine thin gloves
- Attenuate more radiation than comparable gloves
- Offer superb tactile sensitivity
- Comfort and functionality, smooth inside and micro textured outside, and even though they are latex gloves, most of the antigenic proteins have been removed, making them virtually compatible with latex-free standards
- Have reached such dexterity and sensitivity without losing the performances of attenuation that are at top level

Emerson's Radiation Attenuation Examination & Surgical Gloves are used to shield hands from the harmful effects of scattered radiation exposure during fluoroscopic procedures

Meeting EN & ASTM Standards:

EN 455 Surgical gloves EN 420 Gloves: e.g. sizing EN 61331 X-Ray gloves

D3578-09 Standard Specification for Rubber Examination Gloves

EN 421







2777 PPE Reg. (UE) 2016/425

0123 MD acc. to 93/42/EEC

| RR-1: 0.009" / 0.22 mm | | | | | |
|------------------------|-----|-----|-----|--|--|
| Kvp | 60 | 90 | 120 | | |
| Cuff | 45% | 35% | 29% | | |
| Palm | 51% | 40% | 33% | | |
| Finger | 50% | 39% | 32% | | |

| Attenuation Properties EN 61331-1:2014 | | | | | |
|--|-----|-----|-----|--|--|
| RR-2: 0.012" / 0.30 mm | | | | | |
| Kvp | 60 | 90 | 120 | | |
| Cuff | 56% | 44% | 37% | | |
| Palm | 57% | 45% | 38% | | |
| Finger | 57% | 56% | 38% | | |

| RR-3: 0.024" / 0.60 mm | | | | | |
|------------------------|-----|-----|-----|--|--|
| Kvp | 60 | 90 | 120 | | |
| Cuff | 76% | 63% | 55% | | |
| Palm | 75% | 62% | 54% | | |
| Finger | 75% | 62% | 54% | | |